

Artículo/Article		SATÉN ALGODÓN SPANDEX			FINISHED IN SPAIN		Tariff Item: 5208390000 Tariff ItemW:5208290000			
ANÁLISIS FÍSICO / PHYSICAL ANALYSIS										
CARACTERÍSTICAS		RESULTADOS / RESULTS			VALORES / VALUES		TEST			
Nº de Hilo/Thread Count	Urdimbre / Warp		32							
	Trama / Weft		32 + 40D							
Densidad / Density	Urdimbre / Warp		190							
	Trama / Weft		70							
Ligamento / Weave		SATÉN / SATIN						ISO 1833:2006		
Comp. Urd./ Comp. Warp		100% COTTON								
Comp. Tr./ Comp.Weft		95% COTTON / 5% SPDEX								
Total Comp.		97% COTTON / 3% SPANDEX				Simple: No tolerancia Compuesta: +/- 3%				
Ancho Final / Final Width		cm		145-150		+/-2%		ISO 3932:1976		
Peso / Weight		gr/m ²		190		+/-5%		ISO 3801:1977		
Resistencia Rotura/ Breakage	(Kgs.)	Urdimbre		N/A		kgf		ISO: EN ISO 13934-1		
		Trama		N/A		kgf				
Deslizamiento/Seam Slippage (apertura costura/oppening seams)	(mm)	Urdimbre/Warp		N/A		>60 Nw		DIN EN ISO 13936-2		
		Trama / Weft		N/A		>60 Nw				
Resistencia Desgarro / Tear		Urdimbre/Warp (G)		N/A		Trama / Weft		N/A	UNE-EN ISO 13937-1	
Resistencia Abrasion (Ciclos/Cycles)		N/A							NP EN ISO 12947-2:1998	
Pilling (5000 ciclos/cycles)		N/A							NP EN ISO 12945-2	
Encogimiento / Shrinkage	° C	30	% Urdimbre		+/- 3		0 - 3 %		NP EN ISO 5077:2008	
			% Trama		+/- 5					
SOLIDECEZ COLORANTES / SOLIDITY COLORANTS										
SOLIDEZ / SOLIDITY		CA	CO	PA	PES	PAC	WO	< 3 años	>3 años	
Lavado / Washability 30º		4-5						3-4	3-4	UNE-EN ISO 105:C06:2010
Lavado en Seco / Dry Cleaning		4-5								UNE-EN ISO 105:D01:1997
Luz / Light		N/A								UNE-EN ISO 105:B02:2001
Planchado / Ironing		N/A								UNE-EN ISO 105:X11:1997
Sudor Ácido / Acid Sweat		4-5						3-4	3-4	UNE-EN ISO 105:E04:1997
Sudor Básico / Basic Sweat		4-5						3-4	3-4	UNE-EN ISO 105:E04:1997
Agua / Water		N/A						3-4	3	UNE-EN ISO 105:E01:2013
Saliva / Spittle (Infantil/Children's)		N/A						4	3	GB/T 18886:2019
Frote en Seco / Dry Rubbing		4-5						3-4	3	UNE-EN ISO 105:X12:1996
FROTE en Húmedo / Wet Rubbing		3-4						3-4	3	UNE-EN ISO 105:X12:1996
ANÁLISIS QUÍMICO / CHEMICAL ANALYSIS										
CARACTERÍSTICAS		RESULTADOS / RESULTS			VALORES / VALUES		TEST			
pH		N/A			4,0 - 7,5		UNI EN ISO 3071/06			
Formaldehído		N/A			<16ppm		<75ppm		UNE EN ISO 14184-1:1999	
Arlaminas		Conforme/According			Oeko-Tex		20 ppm		UNE 2002/61/CE	
PROHIBIDOS / FORBIDDEN										
Metales Pesados		Conforme/According			Oeko-Tex					
AZO Colorants		Conforme/According			Oeko-Tex		No detectable		(LMBG) (1/4/96)	
Colorantes Alérgicos		Conforme/According			Oeko-Tex		No detectable			
SÍMBOLOS DE LAVADO/ WASH CARE SYMBOLS		g		H		D		L		U
Observaciones:										
Última revisión 05/2022										